

Araldite®

Strength in bonding 2000+

Distributor: www.resinhardener.com



Araldite® 2022 Adhesive

Application	Bonding parts of the Dyson Digital Motor used in the Dyson Airblade™
Substrates bonded	Polyester thermoset on a polycarbonate/ABS alloy
Pretreatments	None
Design of joint	Coaxial. The adhesive is robot applied on X-Y table
Curing conditions	Room temperature (acclimatized area). During cure the parts are held in a jig
Special service conditions	The bonded joints are to resist 248°F and should not be affected when exposed to temperatures of -50°F during transport
Advantages for the customer	The adhesive has excellent gap filling properties, and maintains a high bonding and impact strength at elevated operating temperatures
Advantages over competition	The substrates to be bonded largely limit the choice of adhesives. Araldite® 2022 Adhesive suited its purpose best
Araldite® Adhesive used	Araldite® 2022 Adhesive
Customer location	Great Britain (manufactured in Singapore)

HUNTSMAN ADVANCED MATERIALS GLOBAL DISCLAIMER

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof.

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd ("Huntsman"). The following supersedes Buyer's documents.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLES, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED singly OR IN COMBINATION WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Data and results are based on controlled conditions and/or lab work. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. Buyer should (i) obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product; (ii) take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product; and (iii) comply with and ensure that its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product comply with all safety information contained in the applicable Material Safety Data Sheets, Technical Data Sheets or other instructions provided by Huntsman and all applicable laws, regulations and standards relating to the handling, use, storage, distribution and disposal of and exposure to the Product.

Please note that products may differ from country to country. If you have any queries, kindly contact your local Huntsman representative.

Distributor: www.resinhardener.com



Fast Facts

Araldite® 2022 Adhesive is a two component, room temperature curing, methacrylate adhesive for fast assembly operations on a wide range of substrates including those which can be "difficult to bond".

Good sanding properties

Ideal for bonding thermoplastics

Excellent resistance to petrol and oils

Tolerant to "less than ideal" pretreatment

Gap filling to 4mm

Ideal for bonding:

- ABS
- PVC
- Polycarbonate
- Aluminium
- Steel

HUNTSMAN

Enriching lives through innovation